

Technical Data Sheet


Product Name: Syna Epoxy 510
4-(oxiran-2-ylmethoxy)-N,N-bis(oxiran-2-ylmethyl)aniline

CAS Number: 5026-74-4

EC Number: 225-716-2

Formula: C₁₅H₁₉NO₄

Structure:



Typical Properties:

Term	Specification
Appearance	Yellowish Liquid
Assay	<= 100%
Epoxy Equivalent Weight(Gm/Eq)	95.0-106.0
Viscosity @ 25°C (CPS)	400.0 - 850.0
Total chloride (ppm)	<= 5000
Volatiles	<=1.0%
Package	20kgs/pail, 200kgs/Drum, and 1mt IBC Drum
Shelf Life	Two Years

Storage & Stability:

NEVER store at warm places. Avoid any kind of heat source.
Avoid acidic or basic substances. Avoid direct exposure to sunshine.
Store in a dry location at low temperature, 4°C (40 °F) or below is strongly recommended. Warm the container gradually by letting it stand in an area at room temperature prior to use.